



Head Office: 3rd Floor Einstein Building, 134-134 Union Park, Marabella
Plant Site: Caribbean Drive, Point Lisas Industrial Estate.
Tel: 1 (868) 636-0646/0758; 387-0403/0404;
Morvant Tel: 1 (868) 638-2020/5055; 387-0398/0399

MURAFORM - 204 G

Resin Type:	Melamine Urea Formaldehyde Resin
Appearance.	White free flowing powder
Bulk Density.	0.65 - 0.7 gm/cc
pH.	8.5 - 9.0
Viscosity@ 25 degC (2:1 soln)	2500- 3500 cps
Volatile content.	2.5% (max)

Melamine Resins are specially developed for Warm Water Resistance Grade Plywood, Chip Board, and Flush Door manufacturing.